



## TECHNICAL DATA SHEET

Oxime Silicone is one-component, elastic sealant curing under the influence of humidity from the air, intended for sealing and grouting joints and to protect against moisture.

## APPLICATIONS

|   |
|---|
| grouting floors made of natural stone   |
| sealing sinks with countertops made of natural stone  |
| connecting natural stone with aluminium, concrete, glass  |
| bonding mirrors   |
| sealing building and construction elements made of concrete, wood, metals and synthetic materials |

## BENEFITS

|  |
|--|
| low MEKO   |
| safe for the user  |
| neutral for sensitive surfaces (mirrors, copper alloys, natural stone) |
| does not cause stains, discoloration of natural stone                  |
| low shrinkage  |
| excellent mechanical properties  |
| high flexibility after curing  |
| odourless and chemically neutral                                       |

## APPLICATION CONDITIONS

|                              |          |
|------------------------------|----------|
| Application temperature [°C] | +5 - +40 |
| Surface temperature [°C]     | +5 - +40 |
| Packaging temperature [°C]   | +0 - +25 |

## DIRECTIONS FOR USE

Prior to application, read safety instruction presented in MSDS.

## 1. SURFACE PREPARATION

- Bonding surfaces must be clean, dry (not frosted) free of dust, rust, old loose material, oil, grease, paint and other dirt which reduces the adhesion of the sealant.
- Surfaces best degrease with acetone or ethanol (glass, glaze, metal) or detergent (synthetic materials).
- To avoid dirtiness around the gap and to maintain equal line use adhesive tapes which should be removed immediately after finishing sealing.
- Sealant does not require using primer on most surfaces but on some specific surfaces may have to use it to improve adhesion.
- Joint width should be as to be able to carry movement in range calculated for sealant in question (movement accommodation).
- The sealant bead should not be wider than 25 mm and the minimum joint width should be 6 mm to allow in the construction field proper application and tooling of sealant. The ideal ratio of joint width : depth is 2 : 1.
- For proper design deep joints should be filled with back-up rod.



- In movable joints tripartite sealant adhesion to the surface should be avoided because it can cause its damage. For this purpose if depth of the slots does not allow introduction of polyurethane foam, use dilatation tape or back-up rod. Using foam or tape causes bipartite sealant adhesion and allows proper work with the joint.
- If joints are too shallow to allow backing material to be used, we recommend use of adhesive tape. This acts as a back-up rod to prevent seal in forming of three-sided adhesion.

**2. PRODUCT PREPARATION**

- Prior to application, the product should be conditioned at room temperature.

**3. APPLICATION**

- Cut off the top of the threaded adapter. Screw the nozzle tip on and cut off at a 45° angle, with the diameter equal to the gap width.
- Cut off the top of the foil. Screw the nozzle tip on and cut off at a 45° angle, with the diameter equal to the gap width.
- Squeeze sealant by mechanical or pneumatic gun.
- Treatment make at the time of workability given in the technical data table.
- Applied sealant should be smoothed immediately with a spatula soaked in soapy water for best result.
- Remove masking tape before skin will form.
- Joint should be allowed to fully cure.

**4. WORKS AFTER COMPLETION OF APPLICATION**

- Uncured product should be removed from hands, tools and dirty surfaces with paper towel.
- After curing, remove from hands with water and soap; from tools remove mechanically, or using agent for removing silicones - Silicone Remover.
- DO NOT WASH HANDS WITH SOLVENTS.

**5. REMARKS / RESTRICTIONS**

- Do not apply on wet surfaces.
- Sealant should not be used on bituminous surfaces, partially vulcanized rubber, chloroprene or other construction materials that bleed oils, plasticizers or solvents.
- While planning of the joint, possibility of small discoloration of sealant on some surfaces and under influence of weather conditions should be taken into account.
- Do not use in totally confined spaces where it is not exposed to atmospheric moisture, because the sealant requires atmospheric moisture for curing.
- Sealant is not recommended for joints that are permanently under water, because it can cause physical changes.
- Not suitable for bonding aquariums and terrariums.
- Sealant is not intended for applications involving structural glazing.
- It is not suitable for direct contact with food and medical uses. Sealant was not duly tested and it is not suitable for medical and pharmaceutical applications.
- Do not apply on PE, PP - no adhesion.

Silicone should not be painted.



### TECHNICAL DATA

### TECHNICAL DATA SHEET

| Color       |         |
|-------------|---------|
| White       | RAL9003 |
| Transparent | +       |
| Black       | RAL9005 |
| Brown       | +       |
| Grey        | +       |

| Uncured - tested at 23 °C and 50% relative humidity | Value       |
|---|-------------|
| Density (ISO 2811 -1) [g/ml]                        | 1,01 ± 0,01 |
| Skin formation time [min]                           | 5 - 20      |
| Tack Free [min]                                     | 5 - 10      |
| Curing rate [mm/24h]                                | 2 - 3       |
| Flow from vertical surfaces [+50°C] (ISO 7390) [mm] | 0 - 3       |

| Cured - tested after 4 weeks at 23 °C and 50% relative humidity | Value       |
|---|-------------|
| Shrinkage (ISO 10563) [%]                                       | 7 ± 2       |
| Module at 100% elongation (ISO 8339) [MPa]                      | 0,37 ± 0,07 |
| Elongation at break (ISO 8339) [%]                              | 250 ± 50    |
| Elastic recovery (ISO 7389) [%]                                 | 89 ± 9      |
| Shore A hardness (ISO 868)                                      | 25 ± 2      |
| Temperature resistance [°C]                                     | -50 - +150  |

| Surface                       | Adhesion |
|-------------------------------|----------|
| Aluminium                     | +        |
| Copper                        | +        |
| Cast iron                     | +        |
| Galvanized sheet              | +        |
| Stainless steel               | +        |
| Ceramic tile                  | +        |
| Glass                         | +        |
| Raw wood (pine)               | +        |
| Hard PVC (polyvinyl chloride) | +        |
| PS (polystyrene)              | +        |
| PC (polycarbonate)            | +/-      |
| Brick                         | +        |
| Concrete                      | +        |

|                 |   |
|-----------------|---|
| Granite         | + |
| Sandstone       | + |
| Marble          | + |
| Plaster/Drywall | + |
| Clinker tile    | + |

+ Good adhesion

± Partially adhesive detachment



## TECHNICAL DATA SHEET

All given parameters are based on laboratory tests compliant with internal manufacturer's standards and strongly depend on product hardening conditions (c.a., ambient, surface temperature, quality of used equipment and skills of person applying the product).

**NORMS**

- Product meets requirements of EN 15651-1:2012 F-EXT-INT-CC.
- Product meets requirements of EN 15651-2:2012 G-CC.
- Product meets requirements of EN 15651-3:2012 S.
- Product meets requirements of EN-ISO 11600 : 2004, F&G, 25LM.
- Product meets Hygienic Standard

**TRANSPORT / STORAGE**

Warranted shelf life is 18 months from the manufacturing date when stored in unopened, original package at temperature from +0 °C to +25 °C in a dry place protected from freezing. Product can be transported at low temperatures up to -30 °C for up to 3 weeks, before using the product should be conditioned for 24 hours at +23 °C.

Precautions should be taken when the product after thawing out is frosted again - is resistant to 3 cycles of freezing/thawing out.

**SAFETY AND HEALTH PRECAUTIONS**

For detailed information find Material Safety Data Sheet available at producer upon request. All written or oral information, recommendations and instructions are given according to our best knowledge, tests and experience, in good faith and in compliance with manufacturer's principles. Each user of this material will make sure in every possible way, including verification of the final product in proper conditions, about suitability of the supplied materials for their intended purposes. The manufacturer is not liable for any losses incurred due to inaccurate or erroneous application of the manufacturer's materials.

"The information contained herein is offered in good faith based on STRONGMAN CHEMICALS's research and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information shall not be used in substitution for customer's tests to ensure that STRONGMAN CHEMICALS's products are fully satisfactory for your specific applications. STRONGMAN CHEMICALS's sole warranty is that the product will meet its current sales specifications. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. STRONGMAN CHEMICALS's specifically disclaims any other expressed or implied warranty of fitness for a particular purpose or merchantability. STRONGMAN CHEMICALS's disclaims liability for any incidental or consequential damages. Suggestions of use shall not be taken as inducements to infringe any patent. Technical indications and data appearing in this brochure are based on our current knowledge and experience and we decline all responsibility for consequences derived from inadequate use. Therefore, our guarantee is limited exclusively to the quality of the product supplied. This technical information can be modified without notice. If necessary request it periodically."

**STRONGMAN CHEMICALS**

A Unit of Agape World Pvt. Ltd.

A-305, Patel Paradise CHS, Sector: 35E, Kharghar, Navi Mumbai, Pin: 410210, Maharashtra, India

E-mail : info@strongmanchemicals.com | Web : www.strongmanchemicals.com | Customer Care : 9619783727

Web : www.agape.world

