

ADINO ACOUSTIC PAINTABLE 503

PLASTO ELASTIC DUCTING SEALANT

TECHNICAL DATA SHEET

ADINO ACOUSTIC PAINTABLE 503 is universal, one-component plasto-elastic acrylic sealant, curing by evaporation of water from the mass.

APPLICATION:

- sealing around windows, door frames, sills and balustrades
- sealing cracks and gaps in walls, ceilings and facades
- grouting of corners of walls and ceilings
- protection of polyurethane foams against UV radiation

BENEFITS:

- Odorless and chemically neutral
- possibility of painting and grinding after curing
- possibility of applying multiple layers after curing
- exterior and interior applications

DIRECTIONS FOR USE:

Prior to application, read safety instruction presented in MSDS.

1. SURFACE PREPARATION

- Bonding surfaces must be clean, dry (not frosted) free of dust, rust, old loose material, oil, grease, paint and other dirt which reduces the adhesion of the sealant.
- To avoid dirtiness around the gap and to maintain equal line use adhesive tapes which should be removed immediately after finishing sealing.
- Sealant does not require using primer on most surfaces but on some specific surfaces may have to use it to improve adhesion.
- To increase the adhesion to absorptive substrates, using primer (solution of acrylic in water with ratio 1:2) is recommended.

2. PRODUCT PREPARATION

- Prior to application, the product should be conditioned at room temperature.

3. APPLICATION

- Cut off the top of the threaded adapter. Screw the nozzle tip on and cut off at a 45° angle, with the diameter equal to the gap width.
- Cut off the top of the foil. Screw the nozzle tip on and cut off at a 45° angle, with the diameter equal to the gap width.
- Squeeze sealant by mechanical or pneumatic gun.
- Over dried porous surfaces (plaster, concrete) can be slightly moistened with water to improve the adhesion of the sealant.
- Treatment make at the time of workability given in the technical data table.

STRONGMAN CHEMICALS

Agape World Pvt. Ltd.

A-305, Patel Paradise, Sector- 35E,
Kharghar, Navi Mumbai, PIN: 410210, Maharashtra, India.

E-mail : info@strongmanchemicals.com | Web : www.strongmanchemicals.com |

Customer Care : +91 96197 83727 | Web : www.agape.world |



ADINO ACOUSTIC PAINTABLE 503

PLASTO ELASTIC DUCTING SEALANT

TECHNICAL DATA SHEET

- Applied sealant should be smoothed immediately with a spatula soaked in water for best result.
- Remove masking tape before skin will form.
- Joint should be allowed to fully cure.

4. WORKS AFTER COMPLETION OF APPLICATION

- Clean while uncured with water or water and soap.
- After curing, remove from hands with water and soap; from tools remove mechanically.
- Freshly applied sealant should be protected from rain and direct action of water for minimum 6 hours.
- DO NOT WASH HANDS WITH SOLVENTS.

5. REMARKS / RESTRICTIONS

- Sealant should not be used on bituminous surfaces, partially vulcanized rubber, chloroprene or other construction materials that bleed oils, plasticizers or solvents.
- Sealant is not intended for sealing joints of natural stone, such as granite, sandstone, marble, etc.
- Sealant is not recommended for joints that are permanently under water, because it can cause physical changes.
- Not suitable for bonding aquariums and terrariums.
- Sealant is not intended for applications involving structural glazing.
- It is not suitable for direct contact with food and medical uses. Sealant was not duly tested and it is not suitable for medical and pharmaceutical applications.
- Before painting it is recommended to conduct a trial test, especially in a case of solvent-based paints.
- Do not apply on PE, PP - no adhesion.
- Do not apply on sensitive metal surfaces for example copper and its alloys and silver steel of mirrors.

TECHNICAL DATA:

Color	
White	yes
Grey	yes

Uncured - tested at 23 °C and 50% relative humidity	Value
Density (ISO 2811-1) [g/ml]	1,70 ± 0,01
Skin formation time [min]	10 - 20

Tack Free [min]	5 - 10
Curing rate [mm/24h]	0,5 - 1,0

STRONGMAN CHEMICALS

Agape World Pvt. Ltd.

A-305, Patel Paradise, Sector- 35E,

Kharghar, Navi Mumbai, PIN: 410210, Maharashtra, India.

E-mail : info@strongmanchemicals.com | Web : www.strongmanchemicals.com |

Customer Care : +91 96197 83727 | Web : www.agape.world |



ADINO ACOUSTIC PAINTABLE 503

PLASTO ELASTIC DUCTING SEALANT

TECHNICAL DATA SHEET

Flow from vertical surfaces [+50°C] (ISO 7390) [mm]	0 - 3
---	-------

Cured - tested after 4 weeks at 23 °C and 50% relative humidity	Value
Module at 100% elongation (ISO 37) [MPa]	0,40 ± 0,05
Movement accommodation (ISO 9047) [%]	7,5
Elongation at break (ISO 8339) [%]	37,5 ± 12,5
Elastic recovery (ISO 7389) [%]	20 ± 5
Shore A hardness (ISO 868)	42 ± 2
Temperature resistance [°C]	-20 - +80

Surface	Adhesion
Galvanized sheet	Good
Raw wood (pine)	Excellent
Lacquered wood	Excellent
Hard PVC (polyvinyl chloride)	Excellent
Heterogeneous PVC floor covering	Excellent
PS (polystyrene)	Good
PC (polycarbonate)	Good
Brick	Excellent
Concrete	Good
Plaster/Drywall	Excellent
Cork	Excellent
Foamed PS (Styrofoam)	Excellent

All given parameters are based on laboratory tests compliant with internal manufacturer's standards and strongly depend on product hardening conditions (c.a., ambient, surface temperature, quality of used equipment and skills of person applying the product).

NORM's /ATESTS/ CERTIFICATES:

- Product meets requirements of EN 15651-1:2012 F-EXT-INT.
- Product meets requirements of EN-ISO 11600 : 2004, F, 7,5P.
- Product meets Hygienic Standard.

TRANSPORT / STORAGE

Warranted shelf life is 24 months from the manufacturing date when stored in unopened, original package at temperature from +5 °C to +25 °C in a dry place protected from freezing. Product can

STRONGMAN CHEMICALS

Agape World Pvt. Ltd.

A-305, Patel Paradise, Sector- 35E,
Kharghar, Navi Mumbai, PIN: 410210, Maharashtra, India.

E-mail : info@strongmanchemicals.com | Web : www.strongmanchemicals.com |

Customer Care : +91 96197 83727 | Web : www.agape.world |



ADINO ACOUSTIC PAINTABLE 503 PLASTO ELASTIC DUCTING SEALANT

TECHNICAL DATA SHEET

be transported at low temperatures up to -5 °C for up to 2 weeks, before using the product should be conditioned for 24 hours at +23 °C. Precautions should be taken when the product after thawing out is frosted again - is resistant to 4 cycles of freezing/thawing out.

PRECAUTIONS

For detailed information find Material Safety Data Sheet available at producer upon request. All written or oral information, recommendations and instructions are given according to our best knowledge, tests and experience, in good faith and in compliance with manufacturer's principles. Each user of this material will make sure in every possible way, including verification of the final product in proper conditions, about suitability of the supplied materials for their intended purposes. The manufacturer is not liable for any losses incurred due to inaccurate or erroneous application of the manufacturer's materials.



STRONGMAN

"The information contained herein is offered in good faith based on STRONGMAN CHEMICALS's research and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information shall not be used in substitution for customer's tests to ensure that STRONGMAN CHEMICALS's products are fully satisfactory for your specific applications. STRONGMAN CHEMICALS's sole warranty is that the product will meet its current sales specifications. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. STRONGMAN CHEMICALS's specifically disclaims any other expressed or implied warranty of fitness for a purpose or merchantability. STRONGMAN CHEMICALS's disclaims liability for any incidental or consequential damages. Suggestions of use shall not be taken as inducements to infringe any patent. Technical indications and data appearing in this brochure are based on our current knowledge and experience and we decline all responsibility for consequences derived from inadequate use. Therefore, our guarantee is limited exclusively to the quality of the product supplied. This technical information can be modified without notice. If necessary request it periodically."

STRONGMAN CHEMICALS

Agape World Pvt. Ltd.

A-305, Patel Paradise, Sector- 35E,
Kharghar, Navi Mumbai, PIN: 410210, Maharashtra, India.

E-mail : info@strongmanchemicals.com | Web : www.strongmanchemicals.com |

Customer Care : +91 96197 83727 | Web : www.agape.world |

